



XGrid PET C AM 35 S

Year of last update: **2023**
 Reference norms: **EN 13249, EN 13250, EN 13251, EN 13253, EN 13254, EN 13255, EN 13257, EN 13265**
 Certificate number: **1213-CPR-5555**
 Function: **Erosion control, Reinforcement**



STRUCTURE: 3-dimensional mesh with high void ratio, made with extruded threads welded where they cross coupled with a reinforcing geogrid.

PROPERTIES OF RAW MATERIAL

		<i>tol</i>
Type of product	Geomat	
Raw material (+ UV stabilizer)	PP	
Void ratio	% >95	
Type of reinforcing	Woven grid	
Reinforcing's raw material	PET + polymeric coating	

PHYSICAL/ MECHANICAL CHARACTERISTICS

				<i>tol</i>
Thickness at 2 kPa	EN 9863-1	mm	17	<i>±2</i>
Tensile strenght at maximum load MD	EN ISO 10319	kN/m	≥ 35	
Tensile strenght at maximum load CMD	EN ISO 10319	kN/m	≥ 20	
Extension at max load MD	EN ISO 10319	%	10	<i>+/-2,5</i>
Extension at max load CMD	EN ISO 10319	%	12	<i>+/-2,5</i>

DIMENSIONAL CHARACTERISTICS

				<i>tol</i>
STANDARD DIMENSIONS				
Roll width		m	1,95 - 3,9	<i>±5%</i>
Roll lenght		m	30	<i>±5%</i>

MD: Machine direction

CMD: Cross machine direction



The information given in this data sheet is to the best of our knowledge true and correct. TeMa srl reserves the right to change its product specifications at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.

TeMa Technologies and Materials srl

Via dell'Industria 21 - 31029 Vittorio V.to (TV) Tel. +39.0438.50.31 - Fax +39.0438.50.34.60 - e-mail: info@temacorporation.com - www.temacorporation.com

Rev. giu-23